






**PULL-APART TENSILE STRENGTH TEST RESULTS**

Grab Tensile ASTM D638 Modified

Client Name: Invisible Structures  
 Project Name: --  
 Date Tested: Wednesday, August 11, 2010  
 Tested By: MLM

Job Number: 2441-17  
 Material Type: --  
 Manufacturer: --  
 Sample Type: Pull Test  
 Direction: n/a  
 Grip Separation: 2.2"  
 Width of Sample: 0.18"

Specimen Number	Load (lbs.)	Load(lbs./in)	%Elongation
1	82.67	459.26	13.91
2	83.44	463.54	11.60
3	81.32	451.76	12.11
<b>Average</b>	82.48	458.19	12.54
<b>Standard Deviation</b>	1.07	5.97	1.22



File Name: ISGTPULL  
 Data Entered By: MLM  
 Raw Data Files: IS17GT(1-3).xls

Date: 8/26/2010

Data Checked By: WHR  
 Date: 8/26/10

