




PULL-APART TENSILE STRENGTH TEST RESULTS

Grab Tensile ASTM D638 Modified

Client Name: Invisible Structures
 Project Name: --
 Date Tested: Wednesday, August 11, 2010
 Tested By: MLM

Job Number: 2441-17
 Material Type: --
 Manufacturer: --
 Sample Type: Pull Test
 Direction: n/a
 Grip Separation: 2.2"
 Width of Sample: 0.18"

Specimen Number	Load (lbs.)	Load(lbs./in)	%Elongation
1	82.67	459.26	13.91
2	83.44	463.54	11.60
3	81.32	451.76	12.11
Average	82.48	458.19	12.54
Standard Deviation	1.07	5.97	1.22



File Name: ISGTPULL
 Data Entered By: MLM
 Raw Data Files: IS17GT(1-3).xls

Date: 8/26/2010

Data Checked By: WHR
 Date: 8/28/10

